

Complete Fabricated Snap-Trak® System:

ASTM E-84-84a  
Surface Burning Characteristics of Building Materials

Test Specimen:	Snap-Trak®
Infill:	Polyester
Flame Spread Index:	25
Smoke Developed Value:	240

Test Specimen:	Snap-Trak®
Infill:	Fiberglass
Flame Spread Index:	5
Smoke Developed Value:	90

Test Specimen:	Snap-Trak®
Infill:	Polyester
Flame Spread Index:	6
Smoke Developed Value:	16.5

Typical In-Fill Values:

<u>In-Fill</u>	<u>Flame Spread</u>	<u>Smoke Develop</u>
Polyester:	0	20
Fiberglass:	15	0

Specific testing beyond the above information may be arranged through SoundNice™.